

Raw Material:	Pine (Pinus Sylvestris), Spruce (Picea Abies)						
Thermal modification:	Thermo-D class (+212 °C)						
End use:	Decking, exterior and interior cladding, landscaping						
Moisture:	6 % ± 2 % after production, in our yard						
Allowed planing tolerances:	<table border="0"> <tr> <td>Width</td> <td>± 0.5 mm</td> </tr> <tr> <td>Thickness</td> <td>± 0.5 mm</td> </tr> <tr> <td>Length</td> <td>- 10 mm, +30 mm</td> </tr> </table>	Width	± 0.5 mm	Thickness	± 0.5 mm	Length	- 10 mm, +30 mm
Width	± 0.5 mm						
Thickness	± 0.5 mm						
Length	- 10 mm, +30 mm						

Possible dimensional swelling and shrinkage of 5-6% because of relative air humidity

Allowed deformation tolerances:



Spring
Up to mm per 1 m



Bow
Up to 7.5 mm per 1 m




Twist
Up to 5% of board width per 1 m




Cup
Up to 1% of board width

GRADING

Three sides are graded - the top and the edges. The back is not graded, so any defects there are allowed if they do not compromise the integrity of the board and do not affect the good side of the board.



Pine - heartwood up



Spruce - heartwood down

AB GRADE

This grade is made from AB grade raw material that has been planed but not graded. AB grade may contain up to 30% B grade boards.

A GRADE

The impact of a single defect is assessed by looking at the overall quality of the product.

Completely fallen branches are not allowed on the board, but split branches may occur. The ends of the boards may be cracked. Natural colour variations are allowed, the number of live knots is not limited, the heartwood line is visible. A few flaws are acceptable if the board looks good overall.

After installation, the visible parts of the tongue & groove must be intact. Cracks hidden in the groove are tolerated. 8 cm at the end of the board are not graded (this does not apply to boards with t&g at the ends).

The surface of the boards must be smooth and presentable. A board is not suitable if its general appearance differs significantly from the grade description.

B GRADE

In general, B grade boards have a good appearance. However, individual pieces do not meet A grade requirements because the boards have one or more major defects.

Completely broken pieces are not accepted in B grade.
B grade can easily be upgraded to A grade by cutting off the defects.

C GRADE

C grade consists of rejects that do not meet the parameters of B grade. The boards may be broken, have severe longitudinal cracks, many empty knotholes or other severe mechanical defects.

ATTENTION!

Boards that do not conform to the grade description cannot be cut or otherwise used. Until evaluated, the products must be stored off the ground on a level surface and protected from UV rays. If these instructions are not followed, the boards will not be replaced.

All grades may contain 3% defective boards.

Any quality complaints must be made within 14 days of delivery.

If You need more information, please contact our nearest sales department.



Sound knots
A grade: Allowed, unlimited
B grade: Allowed, unlimited



Knot cluster
A grade: Allowed, unlimited
B grade: Allowed, unlimited



Dead black knots
A grade: Allowed, up to 1/10 board width
B grade: Allowed, unlimited



Knot shakes
A grade: Allowed, up to 5 mm wide & 50 mm long
B grade: Allowed, unlimited



Knot shakes on the edges
A grade: Allowed, up to 1/10 board width
B grade: Allowed, unlimited



Knots with perimeter crack
A grade: Allowed, up to \varnothing 20 mm
B grade: Allowed, unlimited



Knotholes on the sides
A grade: Allowed, up to 15 mm wide
B grade: Allowed, unlimited



Cracked knots
A grade: Allowed, up to 1/10 board width
B grade: Allowed, unlimited



Knotholes
A grade: Not allowed
B grade: Allowed, up to Ø 20 mm,
max 1 pc. x board length, m



Feed-roller marks (from 0.5 mm deep)
A grade: Not allowed
B grade: Allowed, unlimited



Mechanical defects
A grade: Not allowed, except 80 mm
ends of board
B grade: Allowed, up to 300 mm
long, max 0,5 pc. x board length, m



Surface cracks
A grade: Allowed, up to 150 mm long
B grade: Allowed, unlimited



End splits
A grade: Allowed, up to board width
B grade: Allowed, up to 300 mm



Bark knots
A grade: Allowed, up to 1/3 board width
B grade: Allowed, unlimited



Sound heartwood
A grade: Allowed, unlimited
B grade: Allowed, unlimited



Dead heartwood*
A grade: Allowed, unlimited
B grade: Allowed, unlimited
*it is removed if surface is brushed



Resin pockets
A grade: Allowed, up to 200 mm long
B grade: Allowed, unlimited