



UAB BROLIS TIMBER
Inžinierių g. 2, Sergeičikai I, LT-54464 Kauno r., Lithuania
23

EN 14915:2006

Thermally modified (thermo-D) solid soft wood (Scots pine)
panelling and cladding, 19-42 mm x 42-220 mm

The minimum mean density	400 kg/m ³
Minimum overall thickness / minimum	19/11 mm
Intended use:	for exterior use
Reaction to fire class	D-s1,d 0
Thermal conductivity	0,115 W/m K
Biological durability	Class 2
Release of formaldehyde	E1
Content of pentachlorophenol	PCP ≤ 5 × 10 ⁻⁶ n
Resistance to fixing	Pre-drilling – advisable